

Grade: ARMC-CP3015-AL

Manufacturer: Aremco Products, Inc.
Description: Inorganic-ceramic, aqueous-based coating. Curing is not required if product is exposed to a minimum of 500 F within 24-48 hours of application.

PROPERTY	US VALUE		METRIC VALUE	
Type	Inorganic			
Filler	Mixed Oxides			
Temperature Continuous	1500	°F	816	°C
Solids by Weight	58.8	%		
Solids by Volume	12.6	%		
WFT	12 (304.8)	mils (microns)		
DFT	1.5 (38.1)	mils (microns)		
Theoretical Dry Film Coverage	200	@ 1 mil, ft ² /gal	4.9	m ² /liter
Application Temperature MIN	50	°F	10	°C
Application Temperature MAX	90	°F	32	°C
Color	Aluminum			
No. Components	1			
Mixed Viscosity	3,000	@ 25°C, cps		
Specific Gravity	1.7	gms/cc		
Shelf Life	6	months		
Min Air Set	.5	hours		
Heat Cure	200, 2	°F, hours	93, 2	°C, hours
Drying Touch	1	hours		
Drying Handling	1	hours		
Drying Recoat	.5/24	Min/Max hours		