Grade: H37

Manufacturer:

Helwig Carbon

PROPERTY	U	US VALUE		METRIC VALUE	
Туре	Electrographite			1	
Resistivity	18	ohmXinX10 ⁻⁴			
Shore Hardness	75				
Strength	4900	psi	33	mpa	
Voltage Drop	High				
Coefficient of Friction	Very Low				
Film #	2				
Rated Current	80	Amp/in ²	12.4	Amp/cm ²	