

Manufacturer: Helwig Carbon

PROPERTY	US VALUE		METRIC VALUE	
Type	Electrographite			
Resistivity	11	ohmXinX10 ⁻⁴		
Shore Hardness	50			
Strength	3975	psi	27	mpa
Voltage Drop	Medium			
Coefficient of Friction	Low			
Film #	3			
Rated Current	75	Amp/in ²	11.6	Amp/cm ²