

Grade: EC-15

Manufacturer:	Tokai Carbon
Method of Manufacturing:	Isostatically Pressed
Description:	Ultrafine grain isotropic graphite providing fine detailed EDMing while maintaining high tolerances. Excellent finish, high detail burns.
Comparable grades:	AC-15 POCO-200

PROPERTY	US VALUE		METRIC VALUE	
Density	0.0658	lb/in ³	1.82	gr/cm ³
Electrical Resistivity	0.00049	ohm-inch		ohm-m
Flexural Strength	9300	psi	64.1	MPa
Shore Hardness	66			
Average Particle Size	0.00028	in	0.00071	cm