

Grade: ARMC-2330

Manufacturer: Aremco Products, Inc.

PROPERTY	US VALUE		METRIC VALUE	
Specific Gravity	1.43	gms/cc		
Mixed Viscosity	38,000	@ 25°C, cps		
Recommended Cure	1/200	hours/°F		hours/°C
Alternate Cure	.75/200 or .50/400	hours/°F		hours/°C
Temperature Resistance	-76/572	°F	-60/300	°C
CTE	94	in/in °F x 10 ⁻⁶		Microns/m °C
Tensile Strength	425	psi	2.9	MPa
Volume Resistivity	2.0 x 10 ¹⁵	ohm-cm @ RT		
Dielectric Strength	550	volts/mil		ac-kv/mm
Dielectric Constant	3.3	1.0 kHz		
Chemical Resistance	Good			
Color	Red			